

## PRODUCT TESTING LABORATORY

## Preliminary Laboratory Averages Report

\* DATA HAS NOT HAD FINAL REVIEW/APPROVAL: SUBJECT TO CHANGE \*

Report Date: Mar 13 2001 7:46AM      Reported By: WILL, NANCY  
Request: PROC01012      Date Submitted: 03/09/01  
Submitter: S. Laffoon      Date Received: 03/09/01  
Request Type: inh      Date Completed: 03/12/01  
Activity: NOA      Approved By: NOT APPROVED  
Description: NONE - TO TEST ON THE BORGWALT A10.

Categories/Tests	CG2705			CG6240		
	Average	StdDev	N	Average	StdDev	N
Paper						
Permeability, CU	53	6.5	20	17	0.8	17
Permeability, (within band) CU	54	3.5	18	16	1.3	16

  

Categories/Tests	CG6250			CG1591		
	Average	StdDev	N	Average	StdDev	N
Paper						
Permeability, CU	25	2.0	20	36	2.7	20
Permeability, (within band) CU	25	2.8	20	37	4.4	20

## Notations:

CG1591 - MARL LT KS MEN FTB  
CG2705 - MARL MED KS FTB  
CG6240 - BASIC LT KS FTB  
CG6250 - BASIC LT KS FTB

Perm      PPM  
A10

1      Sample #      70